

SID

Factory: Rot am See

Article:

695

ML10

Provided:

Stockburger, Olesja

Customer:

Date:

01.02.2016



Processtechnology: B: undefiniert

Material Text	Mat. Nr.	µm	Stackup	Process overview
A-RS Kupferfolie-018my 330x490mm	50200238	18	VS	1
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	325		2
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		3
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		4
A-RS-FR4-ML-0.30mm-035+035-TG150-HF	50200655	35 300 35	L2 L3	5 A01
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	310		6
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		7
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		8
A-RS-FR4-ML-0.30mm-035+035-TG150-HF	50200655	35 300 35	L4 L5	9 A02
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	310		10
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		11
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		12
A-RS-FR4-ML-0.30mm-035+035-TG150-HF	50200655	35 300 35	L6 L7	13 A03
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	310		14
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		15
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		16
A-RS-FR4-ML-0.30mm-035+035-TG150-HF	50200655	35 300 35	L8 L9	17 A04
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	325		18
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		19
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		20
A-RS Kupferfolie-018my 330x490mm	50200238	18	RS	21

B00

Thickness after Pressing

B00:

3090 µm

Tol+:

320 µm

Tol-:

320 µm

Dmax:

3410 µm

Dmin:

2770 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

3200 µm

Tol+:

320 µm

Tol-:

320 µm

Dmax:

3520 µm

Dmin:

2880 µm

Measuring point: (05) über LM und galv.Cu; beidseitig

nominal:

3096 µm

Version 1.2.14.15

© Würth Elektronik